

# The King of Geomembranes

# HOLD WATER | NO LEAKS | EASY TO INSTALL

T-REX™ SILVER is an engineered multilayered geomembrane used for water retention applications. T-REX™ SILVER has a uniquely designed Recoil™ Film technology to offer an exceptionally high hydrostatic resistance to hold millions of gallons of water. In addition, T-REX™ SILVER product has an innovative Fusion™ coating technology to offer a watertight seal panels. The core woven fabric offers high tensile and tear strength combined with outstanding dimensional stability.

T-REX™ SILVER is stabilized with special UV stabilizers and antioxidants designed to be use for an extended long time exposure water retention applications. T-REX™ SILVER has an excellent flexibility, outstanding durability, stress cracking resistance along with lightweight construction provides an excellent performance in all climates and environmental conditions.

WWW.TREXLINER.COM

**EMAIL: INFO@TREXLINER.COM** 

CALL: 99241 07355

TOLL FREE: 1800 123 8739

TREX

### T-REX™ SILVER Features and Benefits

- Recoil™ Film technology to offer an exceptionally high hydrostatic resistance
- Fusion™ coating technology to offer a watertight seal panels
- Thickness 300 microns (0.30 mm) geomembrane
- · Excellent tensile and tear strength
- · High Puncture, impact and abrasion resistance
- · Ease of welding at low temperatures
- · Special UV and Antioxidant package for long term exposure
- · Outstanding Chemical resistance
- ISI Approved: IS 15351: 2015 CM/L 7800012309
- Meets NSF/ANSI 61 Safe for potable drinking water
- Non-toxic, no PVC or other hazardous materials used in the construction of the geomembrane

## **T-REX™ SILVER Applications**

- Pond Liners
- Oil Field Pit Liners
- Containment Liners
- Golf Course and Decorative Pond Liners
- · Remediation Liners
- Secondary Containment Applications







### T-Rex™ SILVER Technical Data

PROPERTY	TEST/METHOD	T-REX™ SILVER TYPICAL VALUE
Film Structure	Recoil™ Technology	
Fusion Coating	Proprietary Polymer Blend	
Weight (GSM)	ASTM D 5261	260
Nominal Thickness (Micron)	ASTM D 1777	300
Hydrostatic Resistance (PSI)	ASTM D 751	225
Breaking Strength (lbs)	ASTM D 751	MD 280   CD 220
Tear resistance (lbs)	ASTM D 4533	MD 55   CD 45
Puncture resistance (lbs)	ASTM D 751	90
Bursting strength (Ball burst) (PS	I) ASTM D 751	260
Low Temperature Flexibility	ASTM D 2136	-50 °C
Accelerated UV Weathering	ASTM G154	> 90% @ 2000 Hours <sup>†</sup>

All values are ± 10%. †QUV A-340 lamps 8 hrs UV @ 60° C, 4 hrs condensation @ 40°. MD = Machine Direction CD = Cross Direction. The test data is based on an average taken over several production runs and should not be considered or interpreted as minimum or maximum values. Values are typical data and not limiting specifications.

Email: info@trexliner.com | Call : 99241 07355 | Toll Free: 1800 123 8739 | www.trexliner.com